

MAGIC FX bv
Dhr. Jip van Krieken
Industrieweg 16
NL-5281 RW BOXTEL
Nederland



Your notice of	Your reference	Date
01-03-2012		22-03-2012

Analysis Report 12.00918.04

Required tests :

NF P 92-507 (2004)

Identification number	Information given by the client	Date of receipt
T1202629	paper confetti/streamers red	01-03-2012
T1202630	paper confetti/streamers blue	01-03-2012

Pros Van Hoeyland

Order responsible

This report runs to 2 pages and may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.

The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

VAT BE 0459.218.289

Fin. Acc. 210-0472965-45

IBAN BE44 2100 4729 6545

CENTEXBEL-GENT
Technologiepark 7
BE-9052 Zwijnaarde
Tel. + 32 9 220 41 51 • Fax + 32 9 220 49 55
e-mail gent@centexbel.be

CENTEXBEL-BRUSSELS
Montoyerstraat 24 B2
BE-1000 Brussels
Tel. + 32 2 287 08 30 • Fax + 32 2 230 68 15

Reference: T1202629 - paper confetti/streamers red
T1202630 - paper confetti/streamers blue

Classification of materials according to their reaction to fire - "Electric burner"

Date of ending the test 14-03-2012
 Standard used NF P 92-503 (1995)
 Product standard NF P 92-507 (2004)

Deviation from the standard -

Sample thickness ≤ 5 mm

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
 Minimum 7 days or until constant mass is achieved

	Length		Width	
	T12026 29 face A	T12026 30 face B	T12026 30 face A	T12026 29 face B
Hole formation	no	no	no	no
Max. afterflame time (s)	0	0	0	0
Afterglow	yes	yes	yes	yes
Afterglow with propagation in area > 25 cm	no	no	no	no
Damaged length (cm)	25.0	25.0	26.5	24.5
Damaged width (cm) in area >45 cm	0	0	0	0
Flaming molten droplets	no	no	no	no
Non-flaming molten droplets	no	no	no	no
Flaming debris	no	no	no	no
Non-flaming debris	no	no	no	no
Average damaged length (cm)	25.5			
Average damaged width (cm) in area > 45 cm	0			

Classification M1